

**AMENDMENTS TO THE CLAIMS**

The following listing of claims will replace all prior versions of claims in the application:

1. (Previously presented): Ultra opaque coated printable sheet, which comprises a coloured opaque support made from a single ply of paper based on cellulose fibers, said support being coated on at least one of its faces with one or more white pigmented coats such that said printable sheet has an ultra opacity index of more than 92.

2. (Previously presented): Sheet according to claim 1, which has an ultra opacity index of at least 94.

3. (Previously presented): Sheet according to claim 1, wherein its whiteness measured according to standard ISO 11475 is more than 75.

4. (Previously presented): Sheet according to claim 1, wherein the single ply of paper comprises coloured opacifying pigments in bulk.

5. (Previously presented): Sheet according to claim 1, wherein the single ply of paper is covered by a precoat of coloured opacifying pigments.

6. (Previously presented): Process for manufacturing a sheet according to claim 1, wherein at first a coloured opaque support is made from a single ply of paper based on cellulose fibers, and this support is then coated on at least one of its faces with one or several white pigmented coatings such that said sheet is a printable sheet having an ultra opacity index of more than 92.

7. (Previously presented): Process according to claim 6, wherein the deposit of the white pigmented coat(s) is made using a curtain coating head.

8. (Canceled)

9. (Previously presented): Process according to claim 6, wherein opacification is obtained by incorporating opacifying pigments in the paper bulk.

10. (Previously presented): Process according to claim 6, wherein opacification is obtained by depositing a precoat of opacifying pigments either using a size press or using a coating device, on the paper surface.

11. (Previously presented): Process according to claim 10, wherein the coating device used to deposit the precoat of opacifying pigments is a curtain coating head.

12. (Previously presented): Process according to claim 6, wherein the sheet has an ultra opacity index of at least 94.

13. (Previously presented): Process according to claim 6, wherein the opacifying colouring material used is carbon black.

14. (Previously presented): Ultra opaque playing card obtained by the process according to claim 6.

15. (Previously presented): Sheet according to claim 2, which has an ultra opacity index of more than or equal to 94 and a grammage of less than  $300 \text{ g/m}^2$

16. (Previously presented): Sheet according to claim 2, which has an ultra opacity index of more than or equal to 98 and a grammage greater than or equal to  $300 \text{ g/m}^2$ .

17. (Previously presented): Sheet according to claim 3, wherein its whiteness measured according to standard ISO 11475 is greater than or equal to 78.

18. (Previously presented): Process according to claim 11, wherein the deposit of the white pigmented coat(s) is made using a curtain coating head.

Amendment  
Serial No. 10/502,446  
Attorney Docket No. 042573

19. (Previously presented): Ultra opaque playing card obtained using a sheet defined according to claim 1, as its base.

20-26. (Canceled)